

Expo Interior Stucco



DESCRIPTION

USE:

Provides a high quality, long lasting, and durable, color finish for interior walls and ceilings over a hardwall base coat.

COVERAGE:

One 80 pound sack will cover approximately 20 square yards at 1/8 inch thickness.

COMPOSITION:

Expo Interior Stucco is a mechanically blended compound of Keenes gypsum cement, hydrated lime, fine aggregates and other additives, packed in sealed, water-resistant multi-wall bags.

ADVANTAGES:

Expo Interior Stucco provides a uniform, maintenance-free color that does not need painting and can be applied in a wide variety of textures.

COLOR:

Integrally mixed pigment is available in a variety of colors.

SHELF LIFE:

Six (6) months if kept in dry condition.

JOB PROCEDURE:

SUBSTRATE:

The base coat should be rodded and darbed to a true surface. If base coat is dry, dampen lightly and evenly using a fog spray of water to assure even suction.

MIXING:

Mechanically mix with clean water to a stiff consistency for 15 to 20 minutes. Let set for 5 minutes, and then continue mixing, adding water to attain desired consistency.

APPLICATION:

When humidity is low and weather is warm, spray the brown coat with clean water prior to the application of interior stucco in order to control and equalize water absorption and; therefore, obtain even finished color. Hand apply using a trowel. Spread on an even coat, then rubber float (sand finish) or trowel to desired texture.

CURING:

In cold, damp weather, rooms should be temperature controlled. Do not allow to dry too quickly. In dry, windy areas, use fine water spray to dampen.

MATERIAL STANDARDS:

Regular Keenes Cement: Federal Specification SS-C-161B Type F, and Type M, A.S.T.M. Designations C61.
Hydrated Lime: Federal Specification SS-L-351B, Type F and Type M, A.S.T.M. Designations C206-84 (Type S) and C207-79 (Type S), U.B.C. Standard No. 24-18-82.